

Domex 700 MC

Hot rolled, extra high strength, cold forming steel

Product

Domex cold forming steels are thermo-mechanically rolled in modern plants where the heating, rolling and cooling processes are carefully controlled.

The chemical analysis, consisting of low levels of carbon and manganese has precise addition of grain refiners such as niobium, titanium or vanadium. This together with a clean structure, makes Domex Steels the most competitive alternative for cold formed and welded products.

Domex 700 MC with designation D and E meet and exceed the demands for steel S700MC in EN-10149-2.

Applications

The extra high strength steel grades are used in applications such as truck chassis, cranes and earthmoving machines. In these applications, the high strength of the steels is used to save weight and/or to increase the payload.

As a result of this and the good formability of the steels, the total costs can be reduced.

Dimension range

Domex 700 MC is available in the range of sizes tabulated below in as rolled or pickled condition with mill edge.

For material with trimmed edges, the width is reduced by 35 mm.

Some exceptions may occur.

Thickness (mm)	Width (mm)	Length (mm)
2,00 - (3,00)	1000 - 1035	1500 - 13000
3,00 - (4,00)	885 - 1300	1500 - 13000
4,00 - (5,00)	885 - 1400	1500 - 13000
5,00 - (6,00)	885 - 1600	1500 - 13000
6,00 - (7,00)	885 - 1550	1500 - 13000
7,00 - 10,00	885 - 1300	1500 - 13000



Chemical composition

C %	Si %	Mn %	P %	S %	Al %	Nb %	V %	Ti %
max	max	max	max	max	min	max	max	max
0,12	0,10 ¹⁾	2,10	0,025	0,010	0,015	0,09 ²⁾	0,20 ²⁾	0,15 ²⁾

1) If the material is to be hot-dip galvanized, this must be specified in the order.

2) Sum of Nb, V and Ti = 0.22% max.

Mechanical properties

Yield strength R_{eH} N/mm ² min	Tensile strength R_m N/mm ² min - max	Elongation on failure	
		< 3 mm A_{80} % min	≥ 3 mm A_5 % min
700	750 - 950	10	12

Bendability

	Nominal sheet thickness, t		
	≤ 3 mm	3 mm < t ≤ 6 mm	> 6 mm
Min. recommended bending radius (≤ 90°)	0,8 x t	1,2 x t	1,6 x t

Impact strength

The Charpy V-notch test is carried out according to EN 10045-1.

Designation	Test temperature	Energy level
B	Not impact tested	
D	-20°C	40J
E	-40°C	27J

1) Other test temperatures and impact strengths are available subject to special agreement.

Welding

The low contents of carbon, phosphorus and sulphur enable all conventional welding methods to be readily used for Domex 700 MC. No preheating is necessary. A narrow heat affected zone with a somewhat lower hardness is formed immediately adjacent to the weld. However, if normal welding parameters and methods are used, the heat affected zone is of no practical significance.

Tensile test pieces taken across the weld can meet the same minimum tensile strength requirements as the base metal.

There are a large number of matching or over matching filler metals that can be used for welding of Domex 700 MC, which gives a weld that can meet the same minimum tensile strength requirements as the base metal. Some examples of different filler metals that can be used are tabulated below.

Examples of different matching and over matching filler metals

Manual metal arc welding coated electrode	Gas shielded metal arc welding		Manufacturer
	Cored electrode	Wire electrode	
OK 75.75	OK Tubrod 15.27	OK Autrod 13.13	ESAB
-	-	OK 13.29 OK 13.31	-
Filarc 118	PZ6148; PZ6149	-	Filarc
P 110 MR Maxeta 110	-	-	ELGA
Tenacito 75	Fluxofil 42	Carbofil NiMoCr	Oerlikon
Tenacito 80	SAF Dual 270	Spoolcord TD-T90	-

Heat treatment

Stress relief annealing should be carried out within the temperature range of 530 - 580°C. Heat treatment above this range, e.g. normalizing and hot forming, reduce the strength and should be avoided.

Technical service and information

Knowledge Service Center will be pleased to assist with additional information concerning this product and other products from SSAB Tunplåt.

The particulars in this data sheet are correct at the time of going to print and are intended to give general guidance for the use of the product. Subject to changes arising from continual product development. The information and data must not be regarded as guaranteed values, unless specially confirmed in writing.

SSAB Tunplåt AB
SE-781 84 Borlänge
Sweden
Tel +46 243 700 00
Fax +46 243 720 00
office@ssabtunplåt.com
ssabtunplåt.com
ssabdirect.com

Denmark
SSAB Svensk Stål A/S
Tel +45 4320 5000
ssab.dk

Finland
OY SSAB Svenskt Stål Ab
Tel +358-9-686 6030
ssab.fi

France
SSAB Swedish Steel SA
Tel +33 1 55 61 91 00
ssab.fr

Germany
SSAB Swedish Steel GmbH
Tel +49 211 91 25-0
Tel +49 711 6 8784-0
ssab.de

Great Britain
SSAB Swedish Steel Ltd
Tel +44 1905 795794
swedishsteel.co.uk

Italy
SSAB Swedish Steel S.p.A
Tel +39 030 905 881 1
ssab.it

The Netherlands
SSAB Swedish Steel BV
Tel +31 24 67 90 550
ssab.nl

Norway
SSAB Svensk Stål A/S
Tel +47 23 11 85 80
ssab.no

Poland
SSAB Swedish Steel Sp z o.o.
Tel +48 602 725 985

Portugal
SSAB Swedish Steel
Tel +351 256 371 610
ssab.pt

Spain
SSAB Swedish Steel S.L.
Tel +34 91 300 5422
ssab.es

USA
SSAB Swedish Steel Inc.
Tel +1 412-269 21 20
swedishsteel.us

Brazil
SSAB Swedish Steel Ltda.
Tel + 55 41 3014 9070
ssab.com.br

South Africa
SSAB Swedish Steel Pty Ltd
Tel +27 11 822 2570
swedishsteel.co.za

China
SSAB Swedish Steel
Tel +86 10 6466 3441
swedishsteel.cn

Korea
SSAB Swedish Steel Ltd
Tel +82 31 906 2770

