



HARDOX HITUF



HARDOX HITUF

GENERAL PRODUCT DESCRIPTION

The extra-high tough steel for structural wear parts

Hardox® HiTuf is an abrasion-resistant plate with guaranteed impact toughness. With a nominal hardness of 350 HBW, it's a good choice for structural wear parts like thick cutting edges, demolition tools and rippers.

Dimension Range

Hardox HiTuf is available in thicknesses of 40 – 160 mm. Hardox HiTuf is available in widths up to 3350 mm and lengths up to 14630 mm. For thicknesses over 125 mm preferred width is 1650 mm. More detailed information on dimensions is provided in the dimension program.

MECHANICAL PROPERTIES

Thickness (mm)	Hardness Min - Max ¹⁾ (HBW)	Typical yield strength, not guaranteed (MPa)
40.0- 160.0	310- 370	850

¹⁾ Brinell hardness, HBW, according to EN ISO 6506-1, on a milled surface 0.5 – 3 mm below surface. At least one test specimen per heat and 40 tons.

The nominal material thickness will not deviate more than + 15 mm from that of the test specimen.

Hardox is through-hardened. Minimum core hardness is 90 % of the guaranteed minimum surface hardness.

Impact Properties

Variant Name	Minimum impact energy (J) for transverse tests Charpy V 10x10 mm test specimen ²⁾
Hardox HiTuf	40 J /- 40 C

²⁾ Impact testing according to ISO EN 148 per heat and thickness group. Average of three tests. Single value minimum 70% of specified average.

HARDOX HITUF

CHEMICAL COMPOSITION (HEAT ANALYSIS)

C ^{*)} (max %)	Si ^{*)} (max %)	Mn ^{*)} (max %)	P (max %)	S (max %)	Cr ^{*)} (max %)	Ni ^{*)} (max %)	Mo ^{*)} (max %)	B ^{*)} (max %)
0.20	0.60	1.60	0.050	0.020	0.70	2.0	0.70	0.005

The steel is grain refined. ^{*)} Intentional alloying elements.

Maximum carbon equivalent CET (CEV)

Thickness (mm)	40.0 - 70.0 mm	70.1 - 160.0 mm
CET (CEV)	0.38 (0.56)	0.41 (0.66)

$$CET = C + \frac{Mn + Mo}{10} + \frac{Cr + Cu}{20} + \frac{Ni}{40}$$

$$CEV = C + \frac{Mn}{6} + \frac{Cr + Mo + V}{5} + \frac{Cu + Ni}{15}$$

TOLERANCES

More details are given in SSAB's brochure 41-General product information Strenx, Hardox, ArmoX and Toolox-UK or at www.ssab.com.

Thickness

Tolerances according to SSAB's thickness precision guarantee AccuRollTech. AccuRollTech meets the requirements of EN 10 029 Class A, but offers narrower tolerances.

Length and Width

According to SSAB's dimension program. Tolerances conforms to EN 10 029 or to SSAB's standard after agreement.

Shape

Tolerances according to EN 10 029

Flatness

Tolerances according to SSAB flatness tolerances which are narrower than EN 10 029 Class N (steel type L).

Surface Properties

EN 10163-2 Class A Subclass 1

DELIVERY CONDITIONS

The delivery condition is Quenched. The plates are delivered with sheared or thermally cut edges. Untrimmed edges after agreement. Delivery requirements can be found in SSAB's brochure 41-General product information Strenx, Hardox, ArmoX and Toolox-UK or www.ssab.com.

HARDOX HITUF

FABRICATION AND OTHER RECOMMENDATIONS

Welding, bending and machining

Recommendations can be found in our brochures on www.hardox.com or consult Tech Support, techsupport@ssab.com.

Hardox HiTuf is not intend for further heat treatment. It has obtained its mechanical properties by quenching and when necessary by means of subsequent tempering. The properties of the delivery condition cannot be retained after exposure to temperatures in excess of 450°C .

Appropriate health and safety precautions must be taken when welding, cutting, grinding or otherwise working on this product. Grinding, especially of primer coated plates, may produce dust with a high particle concentration.



The UK English version of this document shall prevail in case of discrepancy. Download the latest version of this document at www.ssab.com

Hardox, Strenx, Docol, Dogal, Domex, Toolox, Laser, ArmoX, Ramor, GreenCoat are trademarks of SSAB Technology AB, Sweden

www.ssab.com

DATA SHEET 170 HARDOX HITUF 2013-04-25

SSAB